

TECHN	ICAL DATA SHEET
AC	RYLIC ROOF COATING
Description:	A high quality pure acrylic emulsion-based roof paint.
Chemical Basis:	Acrylic emulsion
Characteristics:	Good UV resistance and does not chalk Durable against normal weather conditions Can be used on cement roof tiles or corrugated iron roofs Easy to clean, removes dirt and grime Water based, easy application, low odour and quick drying.
Intended Uses:	Suitable for direct application to primed or previously painted cement roof tiles and corrugated iron roofs Suitable for correctly prepared and primed galvanized gutters and down pipes, cement plaster, facia boards and timer.
Physical Properties:	
Density	Typical 1.30 – 1.38
Viscosity	Thixotropic
Finish	Low Sheen
Colour Availability	White and various colours
Spreading Rate	3 – 8 sq. meter / litre, dependent on roughness and absorption of surface
PH	8.5 - 9
Flash Point	Non flammable
Shelf Life	Six Months from date of manufacture in unopened original container stored @ below 30 degree C
Pack Size Recommended Surface Preparation:	5LT and 20LT
	Surfaces must be clean, dry and free of grease/oil contaminants. Moisture level must be below 15% for cement surfaces



CK 2008/063408/23 VAT: 4030246120

add the joy of colour to your life

Application Details:	
Mixing Ratio	One pack product, stir with flat paddle until homogenous before use and occasionally during use. Thinning is not recommended
Recommended Application Method	Apply by brush, roller or airless spray
Recommended Dry Film Thickness	2 Coats @ 40 microns per coat
Drying Conditions	Surface Dry30 Mins – 60 MinsHard dry6 Hour
Application Limitations	Do not apply during wet conditions and when temperature is below 5 degree C Metal roofs must not be exposed to rain within 24 hours of application
Health and Safety Data:	
Use	Use in a ventilated area
Protective Clothing	Gloves, goggles and suitable protective clothing should be used.
Storage	Store away from excessive heat and keep out of reach of children.

The information contained herein is accurate and factual to the best of our knowledge and is given in good faith. However, no warranty is implied or expressed in respect of any recommendation or suggestions contained herein. The onus is on the end user to ensure the suitability of this product to meet their requirements. Health and safety procedures when using this product are the end users responsibility.